Determination of Absorption of Morter

Date:

30/12/2007

Client:

مویك میكس (عنایة م/ خالد بسیونی)

Description of sample:

مونة محارة من السمنك البيل , رفيل عجمي , ومادة super soft .

Delivery Date:

10/12/2007

Testing Date:

23/12/2007

Remark:

Materials were delivered by the client on his responsibility.

Note: Sample was taken and delivered by the client.

Results of Sample No. (1):

- Absorption = 5.96%


Tested by

Karem Mahrous, Lab. Tech Checked by

Eng.Ahmed Mokhtar,

Lab. Engineer

المركز المصري الإختيارات (المركز المصري الإختيارات (المركز المصري الإختيارات (Egyptian Testing Center





المركز المصري للإختبارات

Determination of Absorption of Morter

Date:

30/12/2007

Client:

يكس (عناية م/ خالد بسيوني)

Description of sample:

ونة محارة محونة من أسمنت أبيض , رمل عجمى

Delivery Date:

10/12/2007

Casting Date:

10/12/2007

Remark:

Materials were delivered by the elient on his responsibility.

Note: Sample was taken and delivered by the client.

Results of Sample No. (4):

- Absorption = 6.68 %

Tested by

Karem Mahrous, Lab. Tech Checked by

Eng.Ahmed Mokhtar, Lab. Engineer Fauntian Testing Center

